

IN THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. Cancelled
2. Cancelled
3. Cancelled
4. Cancelled
5. Cancelled
6. Cancelled
7. Cancelled
8. Cancelled
9. Cancelled
10. Cancelled
11. Cancelled
12. Cancelled
13. Cancelled
14. Cancelled
15. Cancelled
16. Cancelled
17. Cancelled
18. Cancelled
19. Cancelled
20. (Currently Amended) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:
(A) a copolymer made from styrene and an unsaturated epoxide, as a polyolefin grafted

with an unsaturated epoxide, or a product having two epoxide groups.

(B) a copolymer made from ethylene and an unsaturated carboxylic acid anhydride, and

(C) a copolymer made from an unsaturated carboxylic acid, or an α,ω -aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

21. (Withdrawn) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:

(A) a copolymer made from ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate,

(B) a copolymer made from unsaturated carboxylic acid anhydride, and

(C) a copolymer made from unsaturated carboxylic acid or an α,ω -aminocarboxylic acid.

22. (Withdrawn) A composition according to claim 20, wherein (A) is a copolymer made from ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate.

23. (Withdrawn) A composition according to claim 20, wherein (A) is either a copolymer made from ethylene and an unsaturated epoxide, a polyolefin grafted with an unsaturated epoxide and having two epoxide groups, said product being other than said copolymer and polyolefin, and (C) is a partially or completely hydrolyzed copolymer made from ethylene and an unsaturated carboxylic acid anhydride, a partially or completely hydrolyzed copolymer of a polyolefin grafted with an unsaturated carboxylic acid anhydride, or an α,ω -aminocarboxylic acid.

24. (Withdrawn) A composition according to claim 21, wherein (B) is either a copolymer made from ethylene and an unsaturated carboxylic acid anhydride, or a polyolefin grafted with an unsaturated carboxylic acid anhydride, and (C) is a partially or completely hydrolyzed copolymer made from ethylene and an unsaturated carboxylic acid, a partially or completely hydrolyzed copolymer of a polyolefin grafted with an unsaturated carboxylic acid anhydride, or an α,ω -aminocarboxylic acid.

25. (Withdrawn) A composition according to claim 20, wherein (C) is a copolymer

made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

26. (Withdrawn) A composition according to claim 21, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

27. (Withdrawn) A composition according to claim 22, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

28. (Withdrawn) A composition according to claim 23, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

29. (Withdrawn) A composition according to claim 24, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

30. (Previously Presented) A composition according to claim 20, wherein the thermoplastic polymer is a polyamide or a saturated polyester.

31. (Withdrawn) A composition according to claim 21, wherein the thermoplastic polymer is a polyamide or a saturated polyester.

32. Cancelled

33. (Withdrawn) A composition according to claim 23, wherein (C) is an α,ω -aminocarboxylic acid.

34. (Withdrawn) A composition according to claim 23, wherein (C) is an aminoundecanoic acid.

35. Cancelled

36. (Withdrawn) A composition according to claim 23, wherein (C) is said

copolymer made from ethylene and unsaturated carboxylic acid.

37. (Withdrawn) A composition according to claim 36, wherein (A) is a copolymer made from ethylene and glycidyl methacrylate.

38. (Previously Presented) A composition according to claim 20, wherein (B) is a copolymer made from ethylene and maleic anhydride.

39. (Withdrawn) A composition according to claim 37, wherein (B) is a copolymer made from ethylene and maleic anhydride.

40. (Withdrawn) A composition according to claim 39, wherein (C) is a copolymer made from ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

41. (Currently Amended) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:

(A) a copolymer of ethylene and an unsaturated epoxide, or a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,

(B) a copolymer of ethylene and an unsaturated carboxylic acid anhydride, and

(C) a copolymer of an unsaturated carboxylic acid, or an α,ω -aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

42. (Withdrawn) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of:

(A) an ethylene/alkyl (meth)acrylate/glycidyl (meth)acrylate copolymer,

(B) a copolymer of an unsaturated carboxylic acid anhydride, and

(C) a copolymer of an unsaturated carboxylic acid or an α,ω -aminocarboxylic acid.

43. (Withdrawn) A composition according to claim 20, wherein (A) is a copolymer made from ethylene/methyl acrylate/glycidyl methacrylate and, (B) is a copolymer made from ethylene/ethyl acrylate/maleic anhydride.

44. (Withdrawn) A composition according to claim 43, wherein (C) is a copolymer made from α,ω -amino carboxylic acid or ethylene/alkyl (meth)acrylate/(meth)acrylic acid.

45. (Currently Amended) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of components consisting essentially of:

(A) a copolymer made from ~~ethylene~~ and an unsaturated epoxide, or a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,

(B) a copolymer made from ethylene and an unsaturated carboxylic acid anhydride, and

(C) a copolymer made from an unsaturated carboxylic acid, or an α,ω -aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

46. (Currently Amended) A thermoplastic composition comprising a thermoplastic polymer, having incorporated therein a crosslinked phase from a reaction of components consisting of:

(A) a copolymer made from ~~ethylene~~ and an unsaturated epoxide, or a polyolefin grafted with an unsaturated epoxide, or a product having two epoxide groups,

(B) a copolymer made from ethylene and an unsaturated carboxylic acid anhydride,

(C) a copolymer made from an unsaturated carboxylic acid, or an α,ω -aminocarboxylic acid,

wherein the weight ratio of (C)/(B) is 0.2:1 - 0.5:1.

47. (Previously Presented) A composition according to claim 20, wherein the thermoplastic polymer is a polyamide, (A) is the copolymer made from ethylene and glycidyl methacrylate or the polyolefin is ethylene grafted with glycidyl methacrylate; (B) is the copolymer made from ethylene and maleic anhydride; and (C) is the copolymer made from ethylene and acrylic acid, or ethylene and methacrylic acid.

48. Cancelled

- 49. Cancelled
- 50. Cancelled
- 51. Cancelled
- 52. Cancelled